

High Speed Firing Tray: Silicon carbide (SiC)compound form, If zirconia material touches this tray or there is no High Speed Firing Plate, it will change the color (light YELLOW). Please do not contact the SiC tray with zirconia material. Always should be put on the High Speed Firing Plate. Also, It can not be a cause of this tray itself to GRAY colored zirconia materials. exception: reduction firing CO concentration up 4% or please attempt other company's zirconia material.